

KUKDONG OIL & CHEMICAL CO., LTD.

334-36, YUSAN-DONG, YANGSAN-SI, KYOUNGNAM, KOREA

TEL.(055) 386-0500 FAX.(055) 386-0505

TEST REPORT

Product Name : KD BGR 1

Date :

TEST ITEMS			TEST METHOD	RESULTS
Test	Unit	Condition		
Cone Penetration		Worked	KS M 2032	317
Dropping Point	℃		KS M 2033	198
Copper Strip Corrosion		@100℃ ×24hrs	KS M 2046	Pass
Evaporation Loss	wt%	99℃×22hrs	KS M 2037	0.29
Oil Separation	wt%	100℃×24hrs	KS M 2050	5.58
Sediments	ea/cm ³	10/25/75/125μm	KS M 2048	700/300/50/0
Work Stability		10 ⁵ Strokes	KS M 2051	349
Oxidation Stability	Kg/cm ³	99℃×100hrs	KS M 2049	-
Low Temp Torque	S	gf·cm	KS M 2130	-
	R			-
Humidity		14days	KS M 2130	A Class
H ₂ O Washout Characteristics	%		KS M 2087	3.7

CUSTOMER : _____

Chief Chemist

