

# KUKDONG OIL & CHEMICAL CO., LTD.

334-36, YUSAN-DONG, YANGSAN-SI, KYOUNGNAM, KOREA

TEL.(055) 386-0500 FAX.(055) 386-0505

## TEST REPORT

Product Name : KD BGR 2

Date :

TEST ITEMS			TEST METHOD	RESULTS
Test	Unit	Condition		
Cone Penetration		Worked	KS M 2032	269
Dropping Point	℃		KS M 2033	213
Copper Strip Corrosion		@100℃ × 24hrs	KS M 2046	Pass
Evaporation Loss	wt%	99℃ × 22hrs	KS M 2037	0.24
Oil Separation	wt%	100℃ × 24hrs	KS M 2050	2.4
Sediments	ea/cm <sup>3</sup>	10/25/75/125μm	KS M 2048	700/300/50/0
Work Stability		10 <sup>5</sup> Strokes	KS M 2051	306
Oxidation Stability	Kg/cm <sup>3</sup>	99℃ × 100hrs	KS M 2049	0.3
Low Temp Torque	S	gf·cm	KS M 2130	2000
	R			800
Humidity		14days	KS M 2130	A Class
H <sub>2</sub> O Washout Characteristics	%		KS M 2087	2.5

CUSTOMER : \_\_\_\_\_

\_\_\_\_\_  
Chief Chemist

