

KUKDONG OIL & CHEMICAL CO., LTD.

334-36, YUSAN-DONG, YANGSAN-SI, KYOUNGNAM, KOREA

TEL.(055) 386-0500 FAX.(055) 386-0505

TEST REPORT

Product Name : KD PCGR 00

Date :

TEST ITEMS			TEST METHOD	RESULTS
Test	Unit	Condition		
Cone Penetration		Worked	KS M 2032	408
Dropping Point	℃		KS M 2033	150
Copper Strip Corrosion		@100℃×24hrs	KS M 2046	Pass
Evaporation Loss	wt%	99℃×22hrs	KS M 2037	-
Oil Separation	wt%	100℃×24hrs	KS M 2050	-
Sediments	ea/cm ³	25/75/125 μ m	KS M 2048	-
Work Stability		10 ⁵ Strokes	KS M 2051	-
Apparent Viscosity	P	-10℃, 10 ^{S-1}	KS M 2130	1200
Timken OK Load	Kg		KS M 2130	11.07
Humidity		14days	KS M 2130	A Class
H ₂ O Contents	%		KS M 2035	Trace

CUSTOMER : _____

Chief Chemist

