

KUKDONG OIL & CHEMICAL CO., LTD.

334-36, YUSAN-DONG, YANGSAN-SI, KYOUNGNAM, KOREA

TEL.(055) 386-0500 FAX.(055) 386-0505

TEST REPORT

Product Name : KD EPGR 1

Date :

TEST ITEMS			TEST METHOD	RESULTS
Test	Unit	Condition		
Cone Penetration		Worked	KS M 2032	319
Dropping Point	℃		KS M 2033	206
Copper Strip Corrosion		@100℃×24hrs	KS M 2046	Pass
Evaporation Loss	wt%	99℃×22hrs	KS M 2037	0.17
Oil Separation	wt%	100℃×24hrs	KS M 2050	5.35
Sediments	ea/cm ³	25/75/125 μ m	KS M 2048	300/50/0
Work Stability		10 ⁵ Strokes	KS M 2051	344
Apparent Viscosity	P	-10℃, 10 ^{S-1}	KS M 2130	1300
Timken OK Load	Kg		KS M 2130	18
Humidity		14days	KS M 2130	A Class
H ₂ O Washout Characteristics	%		KS M 2087	3.46

CUSTOMER : _____

Chief Chemist

