

# KUKDONG OIL & CHEMICAL CO., LTD.

334-36, YUSAN-DONG, YANGSAN-SI, KYOUNGNAM, KOREA

TEL.(055) 386-0500 FAX.(055) 386-0505

## TEST REPORT

Product Name : KD EPGR 2

Date :

TEST ITEMS			TEST METHOD	RESULTS
Test	Unit	Condition		
Cone Penetration		Worked	KS M 2032	270
Dropping Point	℃		KS M 2033	214
Copper Strip Corrosion		@100℃×24hrs	KS M 2046	Pass
Evaporation Loss	wt%	99℃×22hrs	KS M 2037	0.22
Oil Separation	wt%	100℃×24hrs	KS M 2050	2.4
Sediments	ea/cm <sup>3</sup>	25/75/125 $\mu$ m	KS M 2048	300/50/0
Work Stability		10 <sup>5</sup> Strokes	KS M 2051	301
Apparent Viscosity	P	-10℃, 10 <sup>S-1</sup>	KS M 2130	2500
Timken OK Load	Kg		KS M 2130	18
Humidity		14days	KS M 2130	A Class
H <sub>2</sub> O Washout Characteristics	%		KS M 2087	2.59

CUSTOMER : \_\_\_\_\_

\_\_\_\_\_  
Chief Chemist

